

PRECONTRAIN

782 S2

┌

┌

782-8100 S2

┌

┌

782-8861 S2

┌

┌

782-8503 S2

PRECONTRAIN

782 S2



▶ MAJOR ADVANTAGES

- Exceptional dimensional stability
- **PVDF varnish: easy maintenance**
- Very good UV resistance
- **optimum weight/ strength ratio**
- high mechanical properties (tensile and tear resistances)

Serge Ferrari

TECHNICAL SPECIFICATIONS


	Preconstraint 782 S2	Preconstraint 782 S2 OP	Standards
Yarn	dtex PES HT	dtex PES HT	TERSUISSE
Weight	780 g/m ²	830 g/m ²	EN ISO 2286-2
Width	250 / 267 cm	250 / 267 cm	
Tensile strength (warp/weft)	350/350 daN/5 cm	350/350 daN/5 cm	EN ISO 1421
Tear strength (warp/weft)	45/40 daN/5 cm	45/40 daN/5 cm	DIN 53.363
Elongation under load (warp/weft)	<1% / <1%	<1% / <1%	NF EN 15619
Adhesion	9/9 daN/5 cm	9/9 daN/5 cm	EN ISO 2411
Finish	weldable PVDF varnish	weldable PVDF varnish	
Flame retardancy	M2/NFP 92-507 - B1/DIN 4102-1 - G1/GOST 30244-94 - 1530.2 et 3/AS NZS- Group 1/AS NZS 3837	M2/NFP 92-507 - B1/DIN 4102-1 - G1/GOST 30244-94 - 1530.2 et 3/AS NZS- Group 1/AS NZS 3837	
Quality management system			ISO 9001
Environment management system			ISO 14001
Guarantees	7 years	7 years	

COLOURS & REFERENCES

Translucent



782-8100 S2



782-8861 S2

Opaque



782-8503 S2

The technical characteristics shown here are average values, given for information only and may be modified (±10%). *Our packaging data are given for information only and may vary as a function of manufacturing conditions.